

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	287681	weld\$4 and (sealant or sealing or insert or interlayer or filler or adhesive)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:07
L2	224	1 and (friction adj (agitation or stir or plunge) or stir adj weld\$4)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:06
L3	2	2 and (sealant or sealing or insert or interlayer or filler or adhesive) near monomer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:07
L4	66	1 and (sealant or sealing or insert or interlayer or filler or adhesive) near monomer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:12
L5	52	4 and (cure\$4 or curing)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:11
L7	47	5 and adhesive	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:09
L8	46	4 and (polymer or polymeri\$8) near monomer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:10
L9	1	8 and (polymer or polymeri\$8) near weld\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:11

L11	2	2 and (polymer or polymeri\$8) near weld\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:11
L12	9	5 and (cure\$4 or curing) near (heat\$4 or laser)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:12
L13	5	12 and laser	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:12
L14	2109	1 and (sealant or sealing or insert or interlayer or filler or adhesive) near (elastomer\$7 or fluoroelastomer\$7 or floroelastomer\$7)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:14
L15	6	14 and 4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:14
L16	2	15 and (fluoroelastomer\$7 or floroelastomer\$7)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2004/09/14 10:14